

DIVISION 7 - THERMAL AND MOISTURE PROTECTION
Section 07900 Joint Sealers
Elastomeric and non-Elastomeric Sealant

Part 1 - General

1.01 Summary

- A. This specification describes the sealing of joints and cracks with a one-component, self-leveling, elastomeric polyurethane sealant.

1.02 Quality Assurance

- A. Manufacturing qualifications: The manufacturer of the specified product shall be ISO 9001:2008 certified and have in existence a recognized ongoing quality assurance program independently audited on a regular basis.
- B. Contractor qualifications: Contractor shall be qualified in the field of concrete repair and protection with a successful track record of 5 years or more. Contractor shall maintain qualified personnel who have received product training by a manufacturer's representative.
- C. Install materials in accordance with all safety and weather conditions required by manufacturer or as modified by applicable rules and regulations of local, state and federal authorities having jurisdiction. Consult Material Safety Data Sheets for complete handling recommendations.

1.03 Delivery, Storage, and Handling

- A. All materials must be delivered in original, unopened containers with the manufacturer's name, labels, product identification, and batch numbers. Damaged material must be removed from the site immediately.
- B. Store all materials off the ground and protect from rain, freezing or excessive heat until ready for use.
- C. Condition the specified product as recommended by the manufacturer.

1.04 Job Conditions

- A. Environmental Conditions: Do not apply material if it is raining or snowing or if such conditions appear to be imminent. Minimum application temperature 40°F (5°C) and rising.
- B. Protection: Precautions should be taken to avoid damage to any surface near the work zone due to mixing and handling of the specified sealant.

1.05 Submittals

- A. Submit two copies of manufacturer's literature, to include: Product Data Sheets, and appropriate Material Safety Data Sheets (MSDS).

1.06 Warranty

- A. Provide a written warranty from the manufacturer against defects of materials for a period of one (1) year, beginning with date of substantial completion of the project.

Part 2 - Products

2.01 Manufacturers

- A. **Sikaflex-1CSL**, as manufactured by Sika Corporation, 201 Polito Avenue, Lyndhurst, NJ 07071 is considered to conform to the requirements of this specification.

2.02 Materials

- A. Polyurethane sealant:
 - 1. The joint sealant shall be a one-component, self-leveling, polyurethane-base material. It shall be applicable in horizontal joints. The sealant shall principally cure under the influence of atmospheric moisture to form an elastomeric substance.
- B. Backer rod or bond breaker tape as approved by engineer.

2.03 Performance Criteria

- A. Properties of the uncured polyurethane sealant:
 - 1. Initial Cure (Tack-Free Time): 1-2 hours
 - 2. Consistency: self-leveling
 - 3. Color: Limestone Gray
- B. Properties of the cured polyurethane sealant:
 - 1. Tensile Properties (ASTM D-412) at 21 days

	<u>Self-Leveling</u>
a. Tensile Strength at break: minimum	300 psi
b. Tensile Elongation: minimum	500%
c. Modulus of Elasticity - 100% Elongation	200 psi, min.
 - 2. Shore A Hardness (ASTM D-2240) at 21 days:
 - a. Self-leveling: 45 +/-5
 - 3. Adhesion in Peel (ASTM C-794)
 - a) Mortar: >15-pli 0% Adhesion Loss
 - b) Aluminum: >15-pli 0% Adhesion Loss
 - 4. Service Range: -40° to 170°F (-40° to 77°C)
 - 5. The sealant shall conform to Federal Specification TT-S-00230C, Type I, Class A.
 - 6. The sealant shall conform to ASTM C-920, Type S, Grade P, Class 25.
 - 7. The sealant shall be capable of ± 25% of the average joint width when tested in accordance to the durability bond test of Federal Specification TT-S-00230C and ASTM C-719.
 - 8. The sealant shall be non-staining.
 - 9. Final Cure: 3 to 5 days.

Note: Tests were performed with material and curing conditions at 71°-75°F and 45-55% relative humidity.

Part 3 - Execution

3.01 Surface Preparation

- A. The joint and adjacent substrate must be clean, dry, sound and free of surface contaminants. Remove all traces of the old sealant, dust, laitance, grease, oils, curing compounds, form release agents and foreign particles by mechanical means, i.e. – sandblasting, etc., as approved by the engineer. Blow joint free of dust using compressed air line equipped with an oil trap.

3.02 Mixing and Application

- A. Joints:
 - 1. Install approved backer rod or bond breaker tape in all joints subject to thermal movement to prevent three-sided bonding and to set the depth of the sealant at a maximum of 1/2 in., measured at the center point of the joint width. Approval of the backer rod or bond breaker tape shall be made by the Engineer.
 - 2. Joints shall be masked to prevent discoloration or application on unwanted areas, as directed by the Engineer. If masking tape is used, it shall not be removed before tooling, yet must be removed before the initial cure of the sealant. Do not apply the masking tape until just prior to the sealant application.
 - 3. Install sealant into prepared joints when the joint is at mid-point of its expansion and contraction cycle.
Self-leveling sealant: Pour or extrude the sealant into the prepared joint in one direction and allow it to flow and level as necessary. Avoid overlapping the sealant to eliminate the entrapment of air. Tool as required to properly fill the joint.
 - 4. Adhere to all limitations and cautions for the polyurethane sealant in the manufacturer's printed literature.
- B. Cracks:
 - 1. Pour or extrude the sealant into the prepared crack in one direction and allow it to flow and level as necessary. Avoid overlapping the sealant to eliminate the entrapment of air. Tool as required to properly fill the crack.
 - 2. Adhere to all limitations and cautions for the polyurethane sealant as stated in the manufacturers printed literature.


3.03 Cleaning

- A. The uncured polyurethane sealant can be cleaned with an approved solvent. The cured polyurethane sealant can only be removed mechanically.
- B. Leave work area in a neat, clean condition without evidence of spillovers onto adjacent areas.

SC-074 Sikaflex®-1CSL Crack Filler

Figure 1 - Sikaflex-1CSL (self-leveling)

1. Pour **Sikaflex-1CSL** into prepared crack, allow to flow and level as necessary. Minimum depth $\frac{1}{4}$ ", $\frac{1}{2}$ " in direct traffic areas.
2. Tool as required to properly finish crack.




SC-074

Sikaflex[®] 1CSL Expansion Joint Filler

Figure 1 - Sikaflex-1CSL(self-leveling)

1. Pour Sikaflex-1CSL into prepared joint, allow to flow and level as necessary. Minimum depth 1/4" to maximum depth 1/2" for working joint.



Concrete Restoration Systems by Sika Corporation, 201 Polito Avenue, Lyndhurst, NJ 07071

The preceding specifications are provided by Sika Corporation as a guide for informational purposes only and are not intended to replace sound engineering practice and judgment and should not be relied upon for that purpose. **SIKA CORPORATION MAKES NO WARRANTY OF ANY KIND, EITHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS OR THE CONTENTS OF THESE GUIDE SPECIFICATIONS.** Sika Corporation assumes no liability with respect to the provision or use of these guide specifications, nor shall any legal relationship be created by, or arise from, the provision of such specifications. **SIKA SHALL NOT BE RESPONSIBLE UNDER ANY LEGAL THEORY TO ANY THIRD PARTY FOR ANY DIRECT OR CONSEQUENTIAL DAMAGES OF ANY KIND ARISING FROM THE USE OF THESE GUIDE SPECIFICATIONS.** The specifier, architect, engineer or design

professional or contractor for a particular project bears the sole responsibility for the preparation and approval of the specifications and determining their suitability for a particular project or application.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available at www.sikaconstruction.com or by calling (201) 933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instructions for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.